


Kendir Özlü Halat Fiber Core

6X37 STANDART TS EN 12385-4	Halat Anma Çapı Diameter of Wire Rope		LÖ Birim Ağırlık FC Unit Weight	En Küçük Kopma Kuvveti Min. Breaking Load	
	(mm)	Tolerans (%)	(kg/m) (kg/m)	Lif Öz Tel Anma Dayanımı (180 kgf/mm ²) Fmin kgf Tensile Strenght	Lif Öz Tel Anma Dayanımı (200 kgf/mm ²) Fmin kgf Tensile Strenght
8			0.221	3400	3775
10			0.346	5310	5900
12			0.498	7645	8490
13			0.585	8970	9965
14			0.678	10400	11560
16			0.886	13585	15095
18			1.121	17195	19105
20			1.384	21225	23590
22			1.675	25685	28540
24			1.993	30570	33965
26			2.339	35875	39860
28			2.713	41605	46230
30	+5		3.114	47760	53070
32	-0		3.543	54340	60380
34			4.001	61350	68165
36			4.484	68775	76420
38			4.996	76630	85145
40			5.536	84910	94345
42			6.103	93615	104015
44			6.698	102740	114155
46			7.321	112290	124770
48			7.972	122270	135855
50			8.650	132670	147410
52			9.356	143495	159440
54			10.089	154745	171940
56			10.850	166420	184910



6X37 STANDART 6(1+6+12+18)

Kullanım Yerleri
(Application Area)

Gemi Bağlama (Mooring)


Sapan Yapımı (Sling)

Denizcilik (Marine)

Genel Mühendislik
(General Engineering)

Çelik Özlü Halat IWRC

6X37 STANDART TS EN 12385-4	Halat Anma Çapı Diameter of Wire Rope		ÇÖ Birim Ağırlık IWRC Unit Weight	En Küçük Kopma Kuvveti Min. Breaking Load	
	(mm)	Tolerans (%)	(kg/m) (kg/m)	Çelik Öz Tel Anma Dayanımı (180 kgf/mm ²) Fmin kgf Tensile Strenght	Çelik Öz Tel Anma Dayanımı (200 kgf/mm ²) Fmin kgf Tensile Strenght
8			0.244	3670	4075
10			0.381	5730	6370
12			0.548	8255	9170
14			0.746	11235	12480
16			0.974	14675	16305
18			1.233	18570	20635
20			1.522	22925	25475
22			1.842	27740	30825
24			2.192	33015	36680
26			2.573	38745	43050
28			2.984	44935	49930
30	+5		3.425	51580	57315
32	-0		3.897	58690	65210
34			4.400	66255	73615
36			4.932	74280	82530
38			5.496	82760	91955
40			6.089	91700	101890
42			6.713	101100	112335
44			7.368	110960	123290
46			8.053	121275	134750
48			8.769	132050	146720
50			9.515	143280	159200
52			10.291	154975	172195
54			11.098	167125	185695
56			11.935	179735	199700



6X37 STANDART 6(1+6+12+18)

Kullanım Yerleri
(Application Area)

Gemi Bağlama (Mooring)

Sapan Yapımı (Sling)

Denizcilik (Marine)

Genel Mühendislik
(General Engineering)