


Kendir Özlü Halat Fiber Core

8X19 SEALE TS EN 12385-5	Normal Çapı Diameter of Wire Rope		En Küçük Kopma Kuvveti Min. Breaking Load		Yaklaşık Ağırlık Weight
	(inch)	(mm)	1370/1770/1570 (N/mm) (kN)		(kg/m)
	3/16	4.76	10.1		0.08
	1/4	6.35	17.7		0.14
	5/16	7.94	28.1		0.22
	-	9.00	35.6		0.28
	3/8	9.50	39.6		0.31
	-	10.00	44.0		0.34
	-	11.00	53.2		0.42
	7/16	11.10	54.2		0.42
	-	12.00	63.3		0.49
	-	12.50	68.7		0.54
	1/2	12.70	70.9		0.55
	-	13.00	74.3		0.58
	-	14.00	86.2		0.67
	9/16	14.30	89.9		0.70
	5/8	16.00	113.0		0.88



8X19 SEALE = 8(1+9+9)


Kullanım Yerleri
(Application Area)

Asansör (Elevators)

Vinçler (Cranes)

Çelik Özlü Halat IWRC

8X19 SEALE TS EN 12385-5	Normal Çapı Diameter of Wire Rope		En Küçük Kopma Kuvveti Min. Breaking Load		Yaklaşık Ağırlık Weight
	(inch)	(mm)	1370/1770 1570 (N/mm) (kN)	1770/1770 1570 (N/mm) (kN)	(kg/m)
	5/16	7.94	36.2	40.8	0.26
	-	9.00	46.6	52.5	0.34
	3/8	9.50	51.9	58.5	0.38
	-	10.00	57.5	64.8	0.42
	-	11.00	69.7	78.6	0.51
	7/16	11.10	71.0	80.1	0.52
	-	12.00	83.0	93.6	0.61
	-	12.50	89.9	101.0	0.66
	1/2	12.70	92.8	105.0	0.68
	-	13.00	97.0	109.0	0.71
	-	14.00	113.0	128.0	0.83
	9/16	14.30	118.0	133.0	0.86
	5/8	16.00	148.0	167.0	1.08
	11/16	17.50	177.0	200.0	1.29
	-	18.00	186.0	210.0	1.36
	3/4	19.10	208.0	234.0	1.52
	-	22.00	279.0	315.0	2.03



8X19 SEALE = 8(1+9+9)

Kullanım Yerleri
(Application Area)

Asansör (Elevators)

Vinçler (Cranes)